

## Jotacote 605

### Product description

This is a two component polyamine cured epoxy coating. It is a surface tolerant, high solids product. This product is tintable in a wide range of colours in Jotun's Multicolor Industry (MCI) system. Specially designed for areas where optimum surface preparation is not possible or desired. Can be used as primer, mid coat, finish coat or as single coat system in atmospheric and immersed environments. Suitable for properly prepared carbon steel, galvanised steel, stainless steel, aluminium, concrete and a range of aged coating surfaces.

### Typical use

Protective:

Recommended for offshore environments, refineries, power plants, bridges, buildings, mining equipment and general structural steel.

### Approvals and certificates

Fire, Australian, AS/NZS 3837.  
Slip Resistance, AS/NZS 4586:2004.  
Potable water, AS/NZS 4020:2005.

Additional certificates and approvals may be available on request.

### Other variants available

Jotacote 605 MIO

Refer to separate TDS for each variant.

### Colours

selected range of colours tinted over Multicolor Industry tinting system (MCI)

## Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	83 ± 2 %
Gloss level (60 °)	ISO 2813	semi gloss (35-70)
Flash point	ISO 3679 Method 1	29 °C
VOC-Solvent Emission Directive	SED (1999/13/EC)	175 g/kg

The provided data is typical for factory produced products, subject to slight variation depending on colour.

All data is valid for mixed paint.

Gloss level: According to Jotun Performance Coatings' definition.

## Recommended film thickness per coat

Film thickness and spreading rate	Dry film thickness (µm)	Wet film thickness (µm)	Theoretical spreading rate (m <sup>2</sup> /l)

Minimum	100	121	8,3
Maximum	250	302	3,3
Typical	125	151	6,6

## Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	St 2 (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Stainless steel	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface and to remove all polish from the surface.	Cleanliness and surface profile corresponding to Sa 2½, Fine G (ISO 8503-2)
Aluminium	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface and to remove all polish from the surface.	Cleanliness corresponding to description of Sa 1 (ISO 8501-1)
Galvanised steel	The surface shall be clean, dry and appear with a rough and dull profile.	Cleanliness corresponding to description of Sa 1 (ISO 8501-1)
Shop primed steel	Clean, dry and undamaged shop primer (ISO 12944-4 6.1)	Sa 2 (ISO 8501-1)
Coated surfaces	Clean, dry and undamaged compatible coating (ISO 12944-4 6.1)	Sa 2½ (ISO 8501-1)
Concrete	Low pressure water washing to a rough, clean, dry and laitance free surface.	Minimum 4 weeks curing. Moisture content maximum 5 %. Low pressure water washing to a rough, clean, dry and laitance free surface.

## Application

### Application methods

The product can be applied by

- Spray: Use airless spray or conventional spray.
- Brush: Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.
- Roller: May be used. Care must be taken to achieve the specified dry film thickness.

### Product mixing ratio (by volume)

Jotacote 605 Comp A	1	part(s)
Jotacote 605 Standard Comp B	1	part(s)
Jotacote 605 Comp A	1	part(s)
Jotacote 605 Fast Cure Comp B	1	part(s)

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 7

### Guiding data for airless spray

Nozzle tip (inch/1000):	15-21
Pressure at nozzle (minimum):	150 bar/2100 psi

## Drying and Curing time

Substrate temperature	5 °C	10 °C	23 °C	40 °C
<b>Jotacote 605 Standard Comp B</b>				
Surface (touch) dry		10 h	4 h	1.5 h
Walk-on-dry		36 h	16 h	8 h
Dried to over coat, minimum		36 h	16 h	8 h
Dried/cured for service		15 d	7 d	4 d
Dried/cured for immersion		7 d	2 d	1 d
<b>Jotacote 605 Fast Cure Comp B</b>				
Surface (touch) dry	12 h	6 h	3 h	1 h
Walk-on-dry	48 h	24 h	8 h	4 h
Dried to over coat, minimum	48 h	24 h	8 h	4 h
Dried/cured for service	15 d	8 d	4 d	3 d
Dried/cured for immersion	10 d	6 d	2 d	1 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85%, and within the DFT range of the product.

**Surface (touch) dry:** The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness. Dry sand sprinkled on the surface can be brushed off without sticking to or causing damage to the surface.

**Walk-on-dry:** Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

**Dried to over coat, minimum:** The shortest time allowed before the next coat can be applied.

**Dried/cured for service:** Minimum time before the coating can be permanently exposed to the intended environment/medium.

**Dried/cured for immersion:** Minimum time before the coating can be permanently immersed in sea water.

## Induction time and Pot life

<b>Paint temperature</b>	<b>23 °C</b>
<b>Jotacote 605 Standard Comp B</b> Pot life	3 h
<b>Jotacote 605 Fast Cure Comp B</b> Pot life	1.5 h

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C
Immersed, sea water	50 °C	60 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat:	epoxy shop primer, inorganic zinc silicate shop primer, zinc epoxy, epoxy, inorganic zinc silicate, epoxy mastic
Subsequent coat:	polyurethane, epoxy, vinyl epoxy, acrylic

## Packaging (typical)

	Volume (litres)	Size of containers (litres)
Jotacote 605 Comp A	10	20
Jotacote 605 Standard Comp B	10	10
Jotacote 605 Fast Cure Comp B	10	10

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

### **Shelf life at 23 °C**

Jotacote 605 Comp A	24 month(s)
Jotacote 605 Standard Comp B	24 month(s)
Jotacote 605 Fast Cure Comp B	24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## **Caution**

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## **Health and safety**

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

## **Colour variation**

Products primarily meant for use as primers and antifoulings may have slight color variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

## **Disclaimer**

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.